




**WELDING CONSUMABLES
FOR HYDRO POWER STATIONS**

Editorial

For beyond 80 years, BÖHLER WELDING has been supplying to component fabricators for the power generating industry. Supported by a strong research and development team, BÖHLER WELDING is also a traditional supplier of specially designed high quality filler metals for the construction and the refurbishment of Francis, Kaplan and Pelton hydro turbines made of 13%Cr 4%Ni or 316L stainless steels. Efficient welding solutions are provided with flux and metal cored wires. The complete range of products for SMAW, GTAW, GMAW and SAW using BÖHLER WELDING consumables means safe and trouble-free plant operation. Excellent references can be given for the construction of penstocks for pumped storage hydro power plants.

Penstocks and bifurcators as high tech components call for competent engineering and top class materials. BÖHLER WELDING's

high strength submerged arc wire/flux combinations or the basic electrodes for vertical down welding – BÖHLER FOX BVD – meet the most stringent mechanical and safety requirements for both the prefabrication and the in-situ circumferential joint welding. When it comes to the orbital welding technology for the in-situ joint welds of penstocks BÖHLER WELDING supplies also the best suitable GTAW wires.


Experienced engineers provide expert advice to optimize your welding procedures. BÖHLER WELDING's worldwide network of sales partners ensures a reliable delivery service and technical advice in more than 70 countries in every continent.

Your nearest sales partner can be found on the Internet at www.boehler-welding.com

BÖHLER WELDING consumables are available in moisture resistant and hermetically sealed packs.



References



Francis turbine made of soft martensitic 13Cr 4Ni stainless steel S41500, 1.4313, welded with BÖHLER CN 13 4-IG by MCE Maschinen- und Apparatebau, Austria.

Selection guide

	Base metals AISI/UNS/ASTM	Welding processes					Page
		SMAW	FCAW	GTAW	GMAW	SAW	
API Pipe steels Re $\geq$ 210 MPa Re $\geq$ 485 MPa	X42-X65	FOX BVD 85					5
	X70, X80	FOX BVD 90					5
	X80	FOX BVD 100					5
High strength steels Re $\geq$ 485 MPa Re $\geq$ 620 MPa Re $\geq$ 690 MPa	A225 Gr. C	FOX EV 65	Ti 60-FD	NiMo 1-IG	NiMo 1-IG	3NiMo 1-UP+BB 24	5, 6
	A517 Gr. A-C	FOX EV 75					6
	USS-T1	FOX EV 85		NiCrMo 2.5-IG	X 70-IG	3NiCrMo 2.5-UP+BB 24	6
Stainless steels Soft martensitic 13Cr 4Ni 16Cr 6Ni Mo Austenitic 19Cr 9Ni 3Mo L	CA6NM	FOX CN 13/4 FOX CN 13/4 SUPRA		CN 13/4-IG	CN 13/4-IG CN 13/4-MC CN 13/4-MC (F)	CN 13/4-UP+BB 203	7 7, 8 7
	–	FOX CN 16/6 M-HD					8
	316L	FOX EAS 4 M FOX EAS 4 M-A	EAS 4 M-FD EAS 4 PW-FD	EAS 4 M-IG	EAS 4 M-IG (Si) EAS 4 M-MC	EAS 4 M-UP+BB 202	8, 9 8, 9 9
Special applications 18Cr 8Ni Mn 23Cr 12Ni L 23Cr 12Ni 2Mo L	dissimilar joints, repair and maintenance	FOX A 7 FOX A 7-A	A 7-FD A 7 PW-FD	A 7 CN-IG	A 7-IG A 7-MC	A 7 CN-UP+BB 203	10, 11 10, 11 11
		FOX CN 23/12-A	CN 23/12-FD CN 23/12 PW-FD	CN 23/12-IG	CN 23/12-IG CN 23/12-MC	CN 23/12-UP+BB 202	11, 12 12
		FOX CN 23/12 Mo-A	CN 23/12 Mo-FD CN 23/12 Mo PW-FD	CN 23/12 Mo-IG			12 12

API Pipe steels

BÖHLER Standard EN AWS	Welding process	Typical analysis %	Typical mechanical properties	Ø mm	Approvals	Characteristics and applications	Base metals
FOX BVD 85 E 46 5 1Ni B 4 5 E8045-P2	SMAW	C 0.05 Si 0.4 Mn 1.1 Ni 0.9	Re 510 N/mm ² Rm 560 N/mm ² A5 27 % Av 170 J 65 J....-50 °C	3.2 4.0 4.5	TÜV-D, GdF, SEPROZ, CE	Basic electrodes for vertical-down welds of large diameter pipelines e.g. penstocks and for structural work. Suitable for filler and cover pass welding in pipeline construction. Deposit is extremely crack resistant, and features high toughness and a very low hydrogen content. The weld deposit of BÖHLER FOX BVD 85 shows an ideal combination between high strength and cryogenic toughness down to -50 °C (-58 °F).	S235J2G3 - S355J2G3, L290NB - L450NB, L290MB - L450MB, P235GH - P295GH API Spec. 5 L: A, B, X42, X46, X52, X56, X60, X65
FOX BVD 90 E 55 5 Z2Ni B 4 5 E9018-G	SMAW	C 0.05 Si 0.3 Mn 1.2 Ni 2.2	Re 600 N/mm ² Rm 650 N/mm ² A5 27 % Av 170 J 80 J....-40 °C	3.2 4.0 4.5	TÜV-D, Statoil, CE, GdF, NAKS, SEPROZ, VNIIST	Special design and development work has enabled this electrode to provide exceptional striking characteristics and the avoidance of start porosity on cover (cap) passes. Due to this and the good welding characteristics this special basic electrode offers easy handling even under field conditions.	L485MB, L555MB API Spec. 5 L: X70, X80
FOX BVD 100 E 62 5 Z2Ni B 4 5 E10018-G	SMAW	C 0.07 Si 0.4 Mn 1.2 Ni 2.3	Re 670 N/mm ² Rm 730 N/mm ² A5 24 % Av 150 J 70 J....-50 °C	4.0 4.5	TÜV-D, SEPROZ, CE		L555MB API Spec. 5 L: X80
BÖHLER Standard EN AWS	Welding process	Typical analysis %	Typical mechanical properties	Ø mm	Approvals	Characteristics and applications	Base metals
FOX EV 65 E 55 6 1 NiMo B 4 2 H5 E8018-GH4R	SMAW	C 0.06 Si 0.3 Mn 1.2 Ni 0.8 Mo 0.35	Re 600 N/mm ² Rm 650 N/mm ² A5 25 % Av 180 J 80 J....-60 °C	2.5 3.2 4.0	TÜV-D, SEPROZ, CE	Basic electrode with high ductility and crack resistance, for high-strength fine-grained steels. Ductile down to -60 °C. Resistant to ageing. Easy to handle in all positions except vertical-down. Preheating and interpass temperature, as well as post weld heat treatment as required by the base metal. Very low hydrogen content (acc. AWS condition HD < 4 ml/100 g).	Constructional steels, pipe- and vessel steels, cryogenic fine-grained steels and special grades. E295-E360, P355NL1- P460NL1, P355 NL2- P460NL2, S380N-S500N, S355NH-S460NH, S380NL-S500NL, S380NL1- S500NL1, 15NiCuMoNb5S (VB 36), 20MnMoNi5-5, 17MnMoV6-4 (VB 35), 22NiMoCr4-7 ASTM: A302 Gr.A-D, A225 Gr.C A572 Gr.65
NiMo 1-IG W 55 6 (GTAW) Mn3Ni1Mo (GTAW) G 55 6 M Mn3Ni1Mo (GMAW) G 55 4 C Mn3Ni1Mo (GMAW) ER90S-G	GTAW GMAW	C 0.08 Si 0.6 Mn 1.8 Ni 0.9 Mo 0.3	Re 620 N/mm ² Rm 700 N/mm ² A5 23 % Av 140 J >47 J....-60 °C	2.4	—	GTAW rod and GMAW wire for high strength, quenched and tempered fine-grained constructional steels. The wire is suited for joint welding in boiler, pressure vessel, pipeline, and crane construction as well as in structural steel engineering.	Pipe steels and fine grained steels, quenched and tem- pered fine-grained steels. S380N-S500N, S380NL-S500NL, S500NC-S550NC, N-A-XTRA 56-70, BH70, PAS600, HSM600, 20MnMoNi5-5 ASTM: A517 Gr.A,B,C,E,F,H,J,K,M,P A225 Gr.C A633 Gr.E A572 Gr.65
Wire: 3 NiMo 1-UP S 3Ni1Mo EF3 (mod.) Flux: BB 24 SA FB 1 65 DC H5	SAW	C 0.09 Si 0.25 Mn 1.65 Ni 0.9 Mo 0.55	Re 580 N/mm ² Rm 650 N/mm ² A5 21 % Av 180 J 60 J....-40 °C	4.0	TÜV-D, CE Wire: TÜV-D, CE	SAW wire/flux combination for joint welding of high strength and low temperature steels. The flux reacts metallurgically Mn-neutral. The sub-arc wire/flux combination produces very good low temperature impact properties down to -40 °C. Excellent slag detachability, smooth beads, good wetting and low hydrogen contents (≤5 ml/100 g) are further important features. The combination is ideally suited for multi-pass welding of thick plates.	

High strenght steels

BÖHLER Standard EN AWS	Welding process	Typical analysis %	Typical mechanical properties	Ø mm	Approvals	Characteristics and applications	Base metals
FOX EV 75 E 62 6 Mn2NiCrMo B 4 2 H5 E10018-GH4R	SMAW	C 0.05 Si 0.4 Mn 1.6 Cr 0.4 Ni 2.0 Mo 0.4	Re 700 N/mm ² Rm 750 N/mm ² A5 23 % Av 140 J >47 J...-60 °C	3.2 4.0	SEPROZ	Basic electrode Mn-Mo-Ni-alloyed with high ductility and crack resistance for high-strength, quenched and tempered fine-grained constructional steels. Suitable for service temperatures at -60 °C to +400 °C. Weld metal recovery approx. 120 %. Easily weldable in all positions except vertical-down. Very low hydrogen content (acc. AWS condition HD < 4 ml/100 g). Preheat, interpass temperature and post weld heat treatment as required by the base metal.	Quenched and tempered fine-grained steels up to 650 N/mm ² yield strength, QT-steels up to 730 N/mm ² tensile strength. UNS: S500N, S460NH, S500NL ASTM: A225 Gr.C, A514 and A517 Gr.A,B,C,E,F,H,J,K,M,P A656, A678 Gr.C
FOX EV 85 E 69 6 Mn2NiCrMo B 4 2 H5 E11018-GH4R	SMAW	C 0.05 Si 0.4 Mn 1.7 Cr 0.4 Ni 2.1 Mo 0.5	Re 780 N/mm ² Rm 840 N/mm ² A5 20 % Av 110 J 60 J...-60 °C	2.5 3.2 4.0 5.0	TÜV-D, DB, ÖBB, SEPROZ, CE	Basic electrode Mn-Ni-Mo-alloyed with high ductility and crack resistant for high-strength fine-grained constructional steels. Low-temperature ductility at -60 °C and resistant to ageing. Easily weldable in all positions except vertical-down. Very low hydrogen content (acc. AWS condition HD < 4 ml/100 g). Preheat, interpass temperature and post weld heat treatment as required by the base metal.	Quenched and tempered fine-grained steels up to 720 N/mm ² yield strength, QT-steels low-alloyed up to 790 N/mm ² tensile strength. S620QL-S690QL, S620QL1, S690QL1 N-AXTRA 56, 63, 70 USS-T1, BH 70 V, HY100
NiCrMo2.5-IG W 69 6 Mn3Ni2.5CrMo ER110S-G	GTAW	C 0.08 Si 0.6 Mn 1.4 Cr 0.3 Ni 2.5 Mo 0.4	Re 810 N/mm ² Rm 910 N/mm ² A5 18 % Av 120 J >47 J...-60 °C	2.4	—	GTAW rod for welding of high strength fine grained constructional steels with strength requirement on low-temperature toughness down to -60 °C, e.g. in marine engineering for the manufacture of LPG tankers.	PAS700, HSM700 ASTM: A514 Gr.F
X 70-IG G 69 5 M Mn3Ni1CrMo ER110S-G	GMAW	C 0.1 Si 0.6 Mn 1.6 Cr 0.25 Ni 1.2 Mo 0.25 V 0.1	Re 800 N/mm ² Rm 900 N/mm ² A5 19 % Av 190 J >47 J...-50 °C	1.0 1.2	TÜV-D, TÜV-A, DB, ÖBB, ABS, BV, DNV, GL, LR, RMR, SEPROZ, CE	GMAW wire for welding of high-strength, heat treated, fine-grained constructional steels with a minimum yield strength of 690 N/mm ² . Also suitable for GTAW hot wire welding for e.g. penstocks. Due to the precise addition of micro-alloying elements X-70-IG wire features excellent ductility and crack resistance in spite of its high strength. Good cryogenic impact energy down to -50 °C.	
Ti 60-FD T 50 6 1Ni P M 1 H5 E81T1-Ni1MH8	FCAW	C 0.06 Si 0.45 Mn 1.2 Ni 0.85	Re >500 N/mm ² Rp >560 N/mm ² A5 >19 % Av >120 J > 47 J...-60 °C (80%Ar/20%CO ₂)	1.2 1.6	LR	Rutile flux cored wire with fast freezing slag system which allows currents up to 250 A in positional welding. It operates in the spray arc transfer without any spatter formation. It provides an easy slag removal, smooth beads with good side wall wetting. Excellent impact properties down to -60 °C.	
Wire: 3 NiCrMo 2.5-UP S 3Ni2.5CrMo EM4(mod.) Flux: BB 24 SA FB 1 65 DC H5	SAW	C 0.06 Si 0.3 Mn 1.5 Cr 0.5 Ni 2.2 Mo 0.5	Re 740 N/mm ² Rm 850 N/mm ² A5 20 % Av 120 J >47 J...-60 °C	3.0 4.0	—	SAW wire/flux combination for joint welding of high strength steels with a minimum yield strength of 690 N/mm ² . Depending on the annealing temperature yield strength of approx. 470-600 N/mm ² are achievable. The flux reacts metallurgically Mn-neutral. The sub-arc wire/flux combination produces very good low temperature impact properties down to -60 °C. Excellent slag detachability, smooth beads, good wetting and low hydrogen contents (≤ 5 ml/100 g) are further important features. The combination is ideally suited for multi-pass welding of thick plates.	

Stainless steels – Soft martensitic

BÖHLER Standard EN AWS	Welding process	Typical analysis %	Typical mechanical properties	Ø mm	Approvals	Characteristics and applications	Base metals
FOX CN 13/4 E 13 4 B 6 2 E410NiMo-15	SMAW	C 0.035 Si 0.3 Mn 0.5 Cr 12.2 Mo 0.5 Ni 4.5	PWHT 600 °C/2 h Re 680 N/mm ² Rm 910 N/mm ² A5 17 % Av 66 J 50 J...-60 °C	2.5 3.2 4.0 5.0	TÜV-D, LTSS, SEPROZ, CE	Basic electrode low-hydrogen suited for similar soft martensitic and martensitic-ferritic rolled, forged, and cast steels. Mainly used in the construction of hydro turbines, compressors. Resistant to corrosion from water, steam, and sea water atmosphere. Thanks to an optimum balance of alloying components the weld deposit yields very good ductility and toughness & cracking resistance despite of its high strength. Excellent operating characteristics, easy slag removal, and smooth bead appearance. Metal recovery approx. 130 %. Positional weldability is offered up to ø 3.2 mm electrodes. Preheating and interpass temperatures of heavy-wall components 100-160 °C.	1.4317 GX4CrNi13-4, 1.4313 X3CrNiMo13-4, 1.4351 X3CrNi13-4, 1.4414 GX4CrNiMo13-4 AISI: ACI Gr. CA6NM UNS: S41500
FOX CN 13/4 SUPRA E 13 4 B 4 2 E410NiMo-15	SMAW	C 0.03 Si 0.3 Mn 0.6 Cr 12.2 Mo 0.5 Ni 4.5	PWHT 600 °C/2 h Re 680 N/mm ² Rm 930 N/mm ² A5 18 % Av 70 J 55 J...-60 °C	3.2 4.0	TÜV-D, SEPROZ, CE	Basic electrode core wire alloyed for welding of similar alloyed soft martensitic steels. Due to an optimum balanced alloying concept the weld deposit offers very good ductility and cracking resistance despite of its high strength. Out of position weldable except vertical down. Preheating and interpass temperatures of heavy-wall components 100-160 °C. Maximum heat input 15 kJ/cm. Post weld heat treatment at 580-620 °C.	
CN 13/4-IG W 13 4 (GTAW) G 13 4 (GMAW) ER410NiMo (mod.)	GTAW GMAW	C 0.01 Si 0.7 Mn 0.7 Cr 12.3 Mo 0.5 Ni 4.7	PWHT 600 °C/8h Re 750 N/mm ² Rm 830 N/mm ² A5 21 % Av 150 J >32 J...-60 °C	2.0 2.4	TÜV-D, SEPROZ, CE	GTAW rod and GMAW wire for welding of similar alloyed soft martensitic steels, with precisely tuned alloying composition for ductile weld metal with best CVN toughness and crack resistance. The preferred gas for MAG welding is Argon +8-10 % CO ₂ .	
CN 13/4-MC T 13 4 MM 2 EC410NiMo (mod.)	GMAW	C <0.025 Si 0.7 Mn 0.9 Cr 12.0 Ni 4.6 Mo 0.6	PWHT 580 °C/8h Re 760 N/mm ² Rm 900 N/mm ² A5 16 % Av 65 J 47 J...-20 °C Shielding gas: Ar + 2.5 % CO ₂	1.2 1.6	SEPROZ	Metal cored wire for welding of similar alloyed soft martensitic steels and cast steels. CN 13/4-MC offers favourable spray or puls arc characteristics, minimum spatter formation, flat and smooth bead profiles, an excellent wetting behaviour and safe penetration as well as best productivity. Best impact values and extra low hydrogen contents (< 4 ml/100 g acc. to AWS 4.3-93). Recommended preheating and interpass temperatures in case of heavy wall thicknesses are 100-160 °C. Maximum heat input 15 kJ/cm. Tempering at 580-620 °C.	
CN 13/4-MC (F) T 13 4 MM 2 EC410NiMo (mod.)	GMAW	C <0.03 Si 0.7 Mn 0.9 Cr 12.2 Ni 4.6 Mo 0.6	PWHT 580 °C/8h Re 700 N/mm ² Rm 880 N/mm ² A5 16 % Av 55 J 47 J...-20 °C Shielding gas: Ar + 2.5 % CO ₂	1.2	—	Metal cored wire for welding of hydro turbine components made of soft martensitic 13 % Cr 4 % Ni alloyed cast steels. BÖHLER CN 13/4-MC (F) offers favourable spray arc or pulsarc characteristics, minimum spatter formation, flat and smooth bead profiles, excellent wetting behaviour and safe penetration. The hydrogen content is low (maximum 5 ml/100 g acc. to AWS A 4.3-93). Significant gains in productivity can be realized by higher deposition rates and reduced post weld grinding when compared to GMAW using solid wires. Welding with conventional or pulsed power sources (preferably slightly trailing torch position, angel appr. 80 °). Recommended stick out 18-20 mm and length of arc 3-5 mm. Recommended preheating and interpass temperatures in case of heavy wall thicknesses are 100-160 °C. Maximum heat input 15 kJ/cm. Tempering at 580-620 °C.	

Stainless steels – Soft martensitic

BÖHLER Standard EN AWS	Welding process	Typical analysis %	Typical mechanical properties	Ø mm	Approvals	Characteristics and applications	Base metals
Wire: CN 13/4-UP S 13 4 ER410NiMo (mod.) Flux: BB 203 SA FB 2 DC	SAW	C 0.015 Si 0.65 Mn 0.7 Cr 11.8 Ni 4.7 Mo 0.5	PWHT 600 °C/2h Re ≥600 N/mm ² Rm ≥800 N/mm ² A5 15 % Av 50 J	3.0	SEPROZ Flux: CE	SAW wire/flux combination for welding similar soft-martensitic steels. The weld deposit featuring very good ductility and CVN toughness as well as high crack resistance. BÖHLER BB 203 is a fluoride-basic, agglomerated flux providing good operating characteristics, smooth beads and a low hydrogen weld metal (HD < 5 ml/100 g). Recommended preheating and interpass temperatures in case of heavy wall thicknesses are 100-160 °C. Maximum heat input 15 kJ/cm. Tempering at 580-620 °C.	
FOX CN 16/6 M-HD E Z16 6 Mo B 6 2 H5 —	SMAW	C 0.03 Si 0.3 Mn 0.6 Cr 15.5 Ni 5.8 Mo 1.2	PWHT 580 °C/4h/air Re 650 N/mm ² Rm 920 N/mm ² A5 15 % Av 42 J HB 340 PWHT 590 °C/8h Re 640 N/mm ² Rm 920 N/mm ² A5 16 % Av 48 J HB 330	2.5 3.2 4.0 5.0	SEPROZ	Basic electrode high efficiency for welding of soft-martensitic forged and cast steels. The high chromium content enhances the corrosion resistance in water, steam and sea atmosphere. Main applications are found in turbines, pumps- and combustion building. Popular in hydro turbine engineering. The electrode shows very good features in regard to arc stability, weld puddle control, slag detachability and seam cleanliness. Suitable for all positions except vertical down (positional welding up to ø 3.2 mm). Metal recovery approx. 135 %. Low hydrogen (HD < 5 ml/100 g) is a essential and necessary prerequisite of this product. The maximum interpass temperature should not exceed 120 °C.	Soft-martensitic forge steels and cast steels, same-alloyed 1.4505 GX5CrNiMo16-5 1.4418 X4CrNiMo16-5

Stainless steels – Austenitic

BÖHLER Standard EN AWS	Welding process	Typical analysis %	Typical mechanical properties	Ø mm	Approvals	Characteristics and applications	Base metals
FOX EAS 4 M E 19 12 3 L B 2 2 E316L-15	SMAW	C 0.03 Si 0.4 Mn 1.2 Cr 18.8 Mo 2.7 Ni 11.8	Re 460 N/mm ² Rm 600 N/mm ² A5 38 % Av 90 J ≥32 J...-120 °C ≥27 J...-196 °C	2.5 3.2 4.0	TÜV-D, TÜV-A, ÖBB, DNV, Statoil, SEPROZ, CE	Basic electrode stainless steel. Designed to produce first class weld deposits. Provides 100 % X-ray safety together with very good root pass and positional welding characteristics. Good gap bridging ability, easy weld pool and slag control. An excellent product for welding on site! Fully alloyed core wire and packed into hermetically sealed tins. Resistant to intergranular corrosion up to +400 °C.	1.4583 X10CrNiMoNb18-12 1.4435 X2CrNiMo18-14-3 1.4436 X3CrNiMo17-13-3 1.4404 X2CrNiMo17-12-2 1.4401 X5CrNiMo17-12-2 1.4571 X6CrNiMoTi17-12-2 1.4580 X6CrNiMoNb17-12-2 1.4409 GX2CrNiMo19-11-2
FOX EAS 4 M-A E 19 12 3 L R 3 2 E316L-17	SMAW	C 0.03 Si 0.8 Mn 0.8 Cr 18.8 Mo 2.7 Ni 11.5	Re 460 N/mm ² Rm 600 N/mm ² A5 36 % Av 70 J ≥32 J...-120 °C	1.5 2.0 2.5 3.2 4.0 5.0	TÜV-D, TÜV-A, ÖBB, DB, DNV, GL, ABS, LR, Statoil, SEPROZ, VUZ, CE	Rutile electrode stainless steel. An acknowledged world leader, noted for its superior welding characteristics. Fully alloyed core wire ensures the most reliable corrosion resistance. Other advantages include high current carrying capacity, minimum spatter formation, self releasing slag, smooth and clean weld profile, safety against formation of porosity due to moisture resistant coating and packaging into hermetically sealed tins and VAC-packs. Resistant to intergranular corrosion up to +400 °C.	AISI: 316 Cb 316 L 316 316 Ti UNS: S31653
EAS 4 M-IG W 19 12 3 L ER316L	GTAW	C 0.02 Si 0.5 Mn 1.8 Cr 18.5 Mo 2.8 Ni 12.3	Re 470 N/mm ² Rm 650 N/mm ² A5 38 % Av 140 J ≥32 J...-196 °C	1.6 2.0 2.4 3.0	TÜV-D, TÜV-A, DNV, GL, DB, ÖBB, SEPROZ, CE	GTAW rod designed to a very precise analysis to create a weld deposit of high purity, superior hot cracking and corrosion resistance. CVN toughness down to -196 °C. Resistant to intergranular corrosion up to +400 °C.	

Stainless steels – Austenitic

BÖHLER Standard EN AWS	Welding process	Typical analysis	Typical mechanical properties	Ø mm	Approvals	Characteristics and applications	Base metals
EAS 4 M-IG (Si) G 19 12 3 L Si ER316LSi	GMAW	C 0.02 Si 0.8 Mn 1.7 Cr 18.4 Mo 2.8 Ni 12.4	Re 450 N/mm ² Rm 630 N/mm ² A5 38 % Av 120 J ≥32 J...-196 °C	0.8 1.0 1.2	TÜV-D, TÜV-A, Statoil, GL, DB, ÖBB, DNV, SEPROZ, CE	GMAW wire designed for first class welding, wetting and feeding characteristics as well as reliable corrosion resistance up to +400 °C and low temperature service down to -196 °C.	
EAS 4 M-MC T 19 12 3 L MM 1 EC316L	GMAW	C <0.03 Si 0.6 Mn 1.4 Cr 18.8 Mo 2.7 Ni 12.2	Re 410 N/mm ² Rm 560 N/mm ² A5 34 % Av 75 J ≥32 J...-196 °C Shielding gas: Ar + 2.5 % CO ₂	1.2	TÜV-D, CE	Metal cored wire for GMAW applicable for same or similar alloyed, stabilized or non stabilized, corrosion resistant CrNiMo-steels. Suitable for service temperatures from -196 °C to +400 °C. This product achieves high productivity and is easy to operate. It provides excellent welding characteristics, smooth almost spatter free weld finish. The wider arc, in comparison to solid wire, will reduce the risk of lack of fusion and is less sensitive against misalignment of edges and different gap widths.	
EAS 4 M-FD T 19 12 3 L R M(C) 3 E316LT0-4(1) ø 0.9 mm T 19 12 3 L P M (C) 1 E316LT1-4(1)	FCAW	C 0.03 Si 0.7 Mn 1.5 Cr 19.0 Mo 2.7 Ni 12.0	Re 400 N/mm ² Rm 560 N/mm ² A5 38 % Av 55 J ≥32 J...-120 °C	0.9 1.2 1.6	TÜV-D, TÜV-A, GL, DB, CWB, ÖBB, LR, SEPROZ, CE	Rutile flux cored wire for downhand welding. This products achieve high productivity and are easy to operate. Self releasing slag, almost no spatter formation and temper discoloration. Smooth weld finish and safe penetration. Suitable for service temperatures from -120 °C to +400 °C.	
EAS 4 PW-FD T 19 12 3 L P M (C) 1 E316LT1-4(1)	FCAW	C 0.03 Si 0.7 Mn 1.5 Cr 19.0 Mo 2.7 Ni 12.0	Re 400 N/mm ² Rm 560 N/mm ² A5 38 % Av 65 J ≥32 J...-120 °C	1.2 1.6	TÜV-D, GL, CWB, SEPROZ, DB, ÖBB, LR, CE	EAS 4 PW-FD is a rutile flux cored wire with fast freezing slag providing excellent positional welding characteristics.	
Wire: EAS 4 M-UP S 19 12 3 L ER316L Flux: BB 202 SA FB 2 DC	SAW	C 0.02 Si 0.6 Mn 1.2 Cr 18.0 Mo 2.8 Ni 12.2	Re ≥350 N/mm ² Rm ≥560 N/mm ² A5 ≥35 % Av ≥80 J ≥32 J...-120 °C	3.0	Wire: TÜV-D, KTA 1408.1 DB, ÖBB, TÜV-A, CE, SEPROZ Flux: TÜV-D, CE	SAW-wire/flux combination of type 316L for multi-pass welding. Smooth beads, easy slag removal without any slag residues and good welding characteristics are very much appreciated by users. BB 202 is a basic, agglomerated flux, providing a low flux consumption. Basicity 2.3 acc. to Boniczewski.	

Special applications

BÖHLER Standard EN AWS	Welding process	Typical analysis %	Typical mechanical properties	Ø mm	Approvals	Characteristics and applications	Base metals
FOX A 7 E 18 8 Mn B 2 2 E307-15 (mod.)	SMAW	C 0.1 Si 0.7 Mn 6.5 Cr 18.8 Ni 8.8	Re 460 N/mm ² Rm 660 N/mm ² A5 38 % Av 90 J ≥32 J...-110 °C	2.5 3.2 4.0 5.0 6.0	TÜV-D, DNV, GL, LTSS, PRS, VUZ, SEPROZ, CE	Basic resp. rutile basic electrodes stainless steel. Very popular for numerous applications. The weld deposit offers exceptionally high ductility and elongation together with crack resistance. There is no fear of embrittlement when operating between -110 °C and +850 °C and can be PWHT without any problems. The deposit will work harden and offers good resistance against cavitation. Ductility is good even after high dilution when welding problem steels or when subjected to thermal shock or scaling. An excellent alloy providing cost effective performance.	For fabrication, -repair and maintenance. Dissimilar joints, tough buffer and intermediate layers prior to hardfacing, 14 % manganese steels, 13 - 17 % Cr heat resistant steels, armour plates, high carbon and quenched & tempered steels, surfacing of gears, valves, turbine blades etc.
FOX A 7-A E Z18 9 Mn Mo R 3 2 E307-16 (mod.)	SMAW	C 0.1 Si 1.5 Mn 4.0 Cr 19.5 Ni 8.5 Mo 0.7	Re 520 N/mm ² Rm 720 N/mm ² A5 35 % Av 75 J ≥32 J...-100 °C	2.5 3.2 4.0 5.0	TÜV-D, SEPROZ, CE	BÖHLER FOX A7-A is suitable for both AC and DC.	
A 7 CN-IG W 18 8 Mn ER307 (mod.)	GTAW	C 0.08 Si 0.8 Mn 7.0 Cr 19.2 Ni 9.0	Re 460 N/mm ² Rm 660 N/mm ² A5 38 % Av 120 J ≥32 J...-110 °C	1.6 2.0 2.4 3.0	TÜV-D, DNV, GL, DB, CE	GTAW rod and GMAW wire. Very popular stainless steel wires for numerous applications. The weld deposit offers exceptionally high ductility and elongation together with crack resistance. There is no fear of embrittlement when operating between -110 °C and +850 °C and can be PWHT without any problems. The deposit will work harden and offers good resistance against cavitation. Ductility is good even after high dilution when welding problem steels or when subjected to thermal shock or scaling. An excellent alloy providing cost effective performance.	
A 7-IG G 18 8 Mn ER307 (mod.)	GMAW	C 0.08 Si 0.9 Mn 7.0 Cr 19.2 Ni 9.0	Re 430 N/mm ² Rm 640 N/mm ² A5 36 % Av 110 J ≥32 J...-110 °C	0.8 1.0 1.2 1.6	TÜV-D, DB, ÖBB, SEPROZ, CE		
A 7-MC T 18 8 Mn MM 1 EC307 (mod.)	GMAW	C 0.1 Si 0.6 Mn 6.3 Cr 18.8 Ni 9.2	Re 400 N/mm ² Rm 600 N/mm ² A5 42 % Av 70 J 30 J...-110 °C Shielding gas: Ar +2.5 % CO ₂	1.2	TÜV-D, DB, CE	Metal cored wire of type T 18 8 Mn/ EC307 for numerous applications. The weld metal offers exceptionally high ductility and elongation together with outstanding crack resistance. There is no fear of embrittlement when operating down to service temperatures of -110 °C or above +500 °C. The scaling resistance goes up to +850 °C. When working at service temperatures above +650 °C please contact the supplier. The weld metal can be post weld heat treated without any problems. The deposit will work harden and offers good resistance against cavitation. Ductility is good even after high dilution when welding problem steels or when subjected to thermal shock or scaling. An excellent alloy providing cost effective performance, excellent welding characteristics, smooth almost spatter free weld finish. The wider arc, in comparison to solid wire, will reduce the risk of lack of fusion and is less sensitive against misalignment of edges and different gap widths.	

Special applications

BÖHLER Standard EN AWS	Welding process	Typical analysis %	Typical mechanical properties	Ø mm	Approvals	Characteristics and applications	Base metals
A 7-FD T 18 8 Mn R M (C) 3 E307T0-G	FCAW	C 0.1 Si 0.7 Mn 6.5 Cr 18.5 Ni 8.8	Re 420 N/mm ² Rm 630 N/mm ² A5 39 % Av 60 J ≥32 J...-100 °C	1.2 1.6	TÜV-D	Rutile flux cored wire. These products achieve high productivity and are easy to operate achieving excellent welding characteristics, self releasing slag, almost no spatter formation and temper discolouration, smooth weld finish and safe penetration. The weld deposit offers exceptionally high ductility and elongation together with crack resistance. There is no fear of embrittlement when operating between -100 °C and +850 °C and can be PWHT without any problems.	
A 7 PW-FD T 18 8 Mn P M (C) 2 E307T1-G	FCAW	C 0.1 Si 0.8 Mn 6.8 Cr 18.8 Ni 9.0	Re 420 N/mm ² Rm 630 N/mm ² A5 39 % Av 65 J ≥32 J...-100 °C	1.2	–	A7 PW-FD is a rutile flux cored wire with fast freezing slag providing positional welding characteristics and fast travel speeds.	
Wire: A 7 CN-UP S 18 8 Mn ER307 (mod.) Flux: BB 203 SA FB 2 DC	SAW	C 0.06 Si 0.8 Mn 6.0 Cr 18.7 Ni 9.0	Re ≥390 N/mm ² Rm ≥620 N/mm ² A5 ≥36 % Av ≥95 J ≥40 J...-100 °C	3.0	Wire: TÜV-D, CE	SAW wire/flux combination for numerous applications. BÖHLER A 7 CN-UP / BB 203 yields a weld deposit offering exceptionally high ductility and elongation together with outstanding crack resistance. There is no fear of embrittlement when operating down to service temperatures of -100 °C or above 500 °C. The scaling resistance goes up to 850 °C. When working at service temperatures above 650 °C please contact the supplier. The weld metal can be post weld heat treated without any problems. The deposit will work harden and offers good resistance against cavitation. Ductility is good even after high dilution when welding problem steels or when subjected to thermal shock or scaling. An excellent alloy providing cost effective performance. Preheating and post weld heat treatment as required by the base metal. BÖHLER BB 203 is a fluoride-basic, agglomerated flux providing good operating characteristics, smooth beads and a low hydrogen weld metal.	
FOX CN 23/12-A E 23 12 L R 3 2 E309L-17	SMAW	C 0.02 Si 0.7 Mn 0.8 Cr 23.2 Ni 12.5	Re 440 N/mm ² Rm 570 N/mm ² A5 40 % Av 60 J ≥32 J...-60 °C	2.5 3.2 4.0 5.0	TÜV-D, DB, ABS, TÜV-A, GL, SEPROZ, DNV, BV, LR, VUZ, ÖBB, CE	Rutile electrode stainless steel. Superior welding characteristics. Can be used on AC or DC. Other advantages include high current carrying capacity, minimum spatter formation, self releasing slag, smooth and clean weld profile, safety against formation of porosity due to the moisture resistant coating and its packaging into hermetically sealed tins or VAC-packs. Operating temperature up to +300 °C and for weld claddings up to +400 °C.	For fabrication, -repair and maintenance
CN 23/12-IG W 23 12 L (GTAW) G 23 12 L (GMAW) ER309L	GTAW GMAW	C ≤0.02 Si 0.5 Mn 1.7 Cr 24.0 Ni 13.2	Re 440 N/mm ² Rm 590 N/mm ² A5 34 % Av 150 J ≥32 J...-120 °C	1.6 2.0 2.4	TÜV-D, TÜV-A, GL, SEPROZ, DB, CE	GTAW rod and GMAW wire designed for good welding, wetting and feeding characteristics as well as good safety after dilution when welding dissimilar joints. Suitable for service temperatures between -120 °C (GTAW) and -80 °C, (GMAW) to +300 °C. For GMAW shielding gas Ar + max. 2,5 % CO ₂ or Ar + max. 1 % O ₂ is recommended.	For welding stainless to mild steel and low alloy steel, for surfacing of mild steel and for root pass welding of clad steel and the first layer of corrosion resistant claddings on mild and low alloyed steels.
CN 23/12-MC T 23 12 L M M 1 EC309L	GMAW	C ≤0.03 Si 0.6 Mn 1.4 Cr 23.0 Ni 12.5	Re 400 N/mm ² Rm 540 N/mm ² A5 32 % Av 90 J ≥32 J...-120 °C Shielding gas: Ar + 2.5 % CO ₂	1.2	–	Metal cored wire of type T 23 12 L / ER309L for welding dissimilar joints between high alloyed Cr- and CrNi(Mo)-steels and mild- or low alloyed steels. BÖHLER CN 23/12-MC is designed for very good welding, wetting and feeding characteristics as well as good safety after dilution when welding dissimilar joints. Suitable for service temperatures between -120 °C and +300 °C. The wider arc, in comparison to solid wire, will reduce the risk of lack of fusion and is less sensitive against misalignment of edges and different gap widths. Preheat and interpass temperature as required by the base metal. Welding with conventional or pulsed power sources (preferably slightly leading torch position, angel appr. 80 °). Recommended stick out 15-20 mm and length of arc 3-5 mm.	

Special applications

BÖHLER Standard EN AWS	Welding process	Typical analysis %	Typical mechanical properties	Ø mm	Approvals	Characteristics and applications	Base metals
CN 23/12-FD T 23 12 L R M (C) 3 E309LT0-4(1) ø 0.9 mm T 23 12 L P M (C) 1 E309LT1-4(1)	FCAW	C 0.03 Si 0.7 Mn 1.4 Cr 23.0 Ni 12.5	Re 400 N/mm ² Rm 540 N/mm ² A5 35 % Av 60 J ≥32 J...-60 °C	0.9 1.2 1.6	TÜV-D, TÜV-A, GL, DB, CWB, ÖBB, LR, SEPROZ, CE	Rutile flux cored wires. These products achieve high productivity and are easy to operate achieving excellent welding characteristics, self releasing slag, almost no spatter formation and temper discolouration, smooth weld finish and safe penetration. Increased travel speeds as well as little demand for cleaning and pickling provide considerable savings in time and money. Suitable for service temperatures from -60 °C to +300 °C.	
CN 23/12 PW-FD T 23 12 L P M (C) 1 E309LT1-4(1)	FCAW	C ≤0.03 Si 0.7 Mn 1.4 Cr 23.0 Ni 12.5	Re 400 N/mm ² Rm 540 N/mm ² A5 35 % Av 65 J ≥32 J...-60 °C Shielding gas: Ar + 18 % CO ₂	1.2 1.6	TÜV-D, LR, ABS, SEPROZ, CWB, DB, ÖBB, GL, CE	CN 23/12 PW-FD is a rutile flux cored wire with fast freezing slag providing excellent positional welding characteristics and fast travel speeds.	
Wire: CN 23/12-UP S 23 12 L ER309L Flux: BB 202 SA FB 2 DC	SAW	C 0.015 Si 0.6 Mn 1.3 Cr 23.5 Ni 13.2	Re >350 N/mm ² Rm >600 N/mm ² A5 >35 % Av >100 J	3.0	Wire: TÜV-D, CE Flux: DNV, CE	SAW wire/flux combination for welding dissimilar joints, Steels with poor weldability and weld surfacings for multi-pass welding. Smooth beads, easy slag release without any slag residues and good welding characteristics. The average ferrite content is 16 FN. Suitable up to service temperatures of +300 °C. BB 202 is a basic, agglomerated flux, providing a low flux consumption. Basicity 2.3 acc. to Boniczewski.	
FOX CN 23/12 Mo-A E 23 12 2 L R 3 2 E309LMo-17	SMAW	C 0.02 Si 0.7 Mn 0.8 Cr 23.0 Mo 2.7 Ni 12.5	Re 580 N/mm ² Rm 720 N/mm ² A5 27 % Av 55 J ≥32 J...-20 °C	2.0 2.5 3.2 4.0 5.0	TÜV-D, TÜV-A, LTSS, DNV, RINA, ABS, VUZ, LR, SEPROZ, BV, NAKS, CE	Rutile stainless steel electrodes. Superior welding characteristics. Can be used on AC or DC. Other advantages include high current carrying capacity, minimum spatter formation, self releasing slag, smooth and clean weld profile, safety against formation of porosity due to the moisture resistant coating and its packaging into hermetically sealed tins or VAC-packs. Operating temperature from -20 °C to +300 °C and for weld surfacings (1 st layer) up to +400 °C.	
CN 23/12 Mo-IG W 23 12 2 L ER309LMo (mod.)	GTAW	C 0.014 Si 0.35 Mn 1.5 Cr 21.5 Mo 2.7 Ni 15.0	Re 470 N/mm ² Rm 640 N/mm ² A5 34 % Av 140 J >32 J...-40 °C	1.6 2.0 2.4	TÜV-D (applied), CE	GTAW rod of type W 23 12 2 L / ER309LMo (mod.) for surfacing low-alloy steels and welding dissimilar joints between duplex and stainless steels with low-alloy steels. When used for surfacing the composition is more or less equal to that of ASTM 316 from the first run. BÖHLER CN 23/12 Mo-IG is designed for very good welding and wetting characteristics and ensuring a high resistance against cracking. Suitable for service temperatures between -40°C and +300°C.	
CN 23/12 Mo-FD T 23 12 2 L R M (C) 3 E309LMoT0-4(1) ø 0.9 mm T 23 12 2 L P M (C) 1 E309LMoT1-4(1)	FCAW	C 0.03 Si 0.6 Mn 1.4 Cr 23.0 Mo 2.7 Ni 12.5	Re 500 N/mm ² Rm 700 N/mm ² A5 30 % Av 55 J ≥32 J...-60 °C	0.9 1.2 1.6	TÜV-D, TÜV-A, ÖBB, DB, GL, DNV, LR, ABS, RINA, SEPROZ, CE	Rutile flux cored wires. These products achieve high productivity and are easy to operate achieving excellent welding characteristics, self releasing slag, almost no spatter formation and temper discolouration, smooth weld finish and safe penetration. Increased travel speeds as well as little demand for cleaning and pickling provide considerable savings in time and money. Suitable for service temperatures from -60 °C to +300 °C. It can also be used for 316L weld surfacing of un- or low alloyed base metals with very economic results. CN 23/12 Mo PV-FD is a rutile flux cored wire with fast freezing slag providing excellent positional welding characteristics and fast travel speeds.	
CN 23/12 Mo PW-FD T 23 12 2 L P M (C) 1 E309LMoT1-4(1)	FCAW	C 0.03 Si 0.7 Mn 1.4 Cr 23.0 Mo 2.7 Ni 12.5	Re 530 N/mm ² Rm 720 N/mm ² A5 32 % Av 65 J ≥32 J...-60 °C Shielding gas: Ar + 18 % CO ₂	1.2	TÜV-D, SEPROZ BV, LR, DNV, CE		

References




References

Close up view on a Francis turbine.
Special jobs need special filler metals!



© AGROUNZ

Kaplan turbine made of 13Cr 4Ni
stainless steel S 41500, 1.4313



© VAtect Hydro

References

Spiral case of the hydropower plant Goldisthal, Germany, in the workshops in Ravensburg




© VA Tech Hydro

Penstock Kaprun, Austria. MCE staff control the fully mechanized GTAW hot wire process



**Prefabrication of the Penstock Kaprun, Austria
Steel grade S 690 Q, ASTM A514 Gr.F, SAW
BÖHLER 3NiCrMo2,5UP+BB24**



**Penstock MINGTAN, Vietnam with 6,8m diameter
and 4 km length made of high strength steel up to
YS 690 MPa welded with BÖHLER FOX EV 85**

Details regarding the nature and application purposes of our products are intended for the information of the user. The data concerning the mechanical properties always refers to the all weld metal deposit in accordance with the applicable standards. In the area of the weld joint, the weld metal properties are influenced by the base metal, the welding position and the welding parameters. A guarantee of the suitability for a specific type of application requires in each individual case an implicit agreement in writing.

Subject to change without notice.

Published by BÖHLER WELDING

Böhler Schweißtechnik Austria GmbH

Böhler-Welding-St. 1

8605 Kapfenberg / AUSTRIA

☎ +43 (0) 3862-301-0

☎ +43 (0) 3862-301-95193

✉ postmaster.bsga@bsga.at

www.boehler-welding.com

Your partner:

www.boehler-welding.com